

IN THE CLAIMS:

Amend the claims as follows:

Claim 1 (Currently amended): An ink jet recording paper which comprises a neutral base paper comprising a wood pulp as a starting material on which is coated a coating solution consisting essentially of a diaminostilbene-disulfonic acid derivative (A) as a fluorescent brightening agent, a binder consisting of a water-soluble binder and water, and a ~~polyvinyl alcohol-cation monomer graft polymer~~ graft copolymer of polyvinyl alcohol and polydiallyldimethyl-ammonium chloride (B) as a cationic polymer fixing agent, a mixing ratio A:B in solid coating amount being within the range of 1:6-2:3, said coated paper having an ISO brightness of not less than 95% and a fluorescence intensity of 7-15% measured by a method specified in JIS P-8148 using a xenon flash lamp as a light source.

Claim 2 (Previously presented): An ink jet recording paper according to claim 1, wherein the neutral base paper is made using calcium carbonate as a filler and an ash content of the base paper is 5-20% measured in the same manner as specified in JIS P-8128, except that the incineration treatment is carried out at 500° for 4 hours.

3. (Canceled):

4. (Original): An ink jet recording paper according to claim 1, wherein the coating

solution is coated using an on-machine size press of a paper machine.

5. (Original): An ink jet recording paper according to claim 1, wherein the wood pulp contains a waste paper pulp.

Claim 6 (Previously presented): An ink jet recording sheet according to claim 1, wherein the coating solution further contains a coloring dye or a coloring pigment.